DOI: 10.3901/JME.2021.09.001

人工肌肉驱动器研究进展综述*

邢志广^{1,2} 林俊^{1,2} 赵建文^{1,2}

(1. 哈尔滨工业大学(威海)机器人研究所 威海 264209;
2. 威海市机器人与智能装备产业研究院 威海 264209)

摘要: 人工肌肉通常是指能够在外界物理或化学刺激下发生伸缩、膨胀、弯曲、扭转等运动并对外做功的柔性材料或器件,借助人工肌肉驱动可大幅提高机器人的柔顺适应能力和人机力学交互的舒适性。人工肌肉的发展已有超过六十年的历史,其激励方式也包括电、热、内压等多种形式;尝试从人工肌肉种类、驱动原理、性能指标、应用场合、发展趋势等方面对人工肌肉相关内容予以较全面的综述,以期为机器人或其他领域感兴趣的学者提供参考和对比。

关键词: 柔性驱动器; 人工肌肉; 软驱动器; 软体机器人

中图分类号: TP242

Overview of the Artificial Muscle Actuators

XING Zhiguang^{1,2} LIN Jun^{1,2} ZHAO Jianwen^{1,2}

(1. Robotics Institute, Harbin Institute of Technology (Weihai), Weihai 264209;
2. Industrial Research Institute of Robotics and Intelligent Equipment, Weihai 264209)

Abstract: Artificial muscle usually refers to a flexible material or device that can perform movements such as extension, expansion, bending, and twisting under external physical or chemical stimulation and do work to external object. The artificial muscle can greatly improve the robot's flexibility and adaptability, and human-machine interaction. The development of artificial muscles has a history of more than sixty years, and the methods to stimulate them are also various, such as by electricity, by heat, by internal pressure, etc. This research attempts to give a review of artificial muscles in driving principle, performances, applications and development trends, with a view to provide references and comparisons for roboticists and other researchers who are interesting in it.

Key words: soft actuator; artificial muscle; soft actuator; soft robotics

0 前言

哺乳动物、昆虫、鸟类、鱼类等多种生物都是靠生物肌肉系统来驱动身体完成走、跑、跳、爬、飞、游等运动,蒸汽机、内燃机、电动机可看成人造机械系统的“肌肉”。目前,机器人的“肌肉”多为刚性器件,在柔顺性、功率密度、能量利用效率、结构功能一体化等方面与生物肌肉相比还有较大差距^[1],因此众多学者致力于研制出能够媲美生物肌肉性能的人工肌肉^[2-5]。

人工肌肉^[1, 6-8]通常是指能够在外界物理或化学

刺激下(机械应力、电、磁、热、光、生物电、分解反应等)发生伸缩、膨胀、弯曲、扭转等运动并对外做功的柔性材料或器件^[9-10],比如形状记忆材料、压电材料、电活性聚合物(Electroactive polymer, EAP)、光致变形材料、气动软体驱动器等。人工肌肉的应力-应变、响应速率、功率密度、能量效率、直驱能力、生命周期等都是大家非常关注的性能指标。

应力-应变能力: 应力输出能力是在一定的应变下机器人单位截面积能够输出的力,相当于生物肌肉的拉力;而应变能力是人工肌肉在激活变形后尺寸在预期运动方向上相对原始尺寸的比例,比如电致应变等性能。

响应速度: 指人工肌肉在激励下变形的快慢,通常用人工肌肉连续运动时可实现的动作频率来衡量,以 Hz 为单位。

* 国家自然科学基金重大研究计划培育(91648106)和山东省自然科学基金面上(ZR2016EEM16)资助项目。20200522 收到初稿,20201118 收到修改稿

功率密度: 单周期内人工肌肉做功与重量(或体积)的比值, 如 W/g (W/mm^3)。

能量效率: 一般指人工肌肉输出做功与输入能量的百分比。

直驱能力: 不同于电动机或内燃机驱动系统的齿轮减速、螺杆传动、液压传动、绳索皮带传动等, 生物肌肉一般不经过速度变换来提升驱动力, 而是直接驱动骨骼运动; 这种直驱能力带来更高的柔顺性和更快的响应能力。人工肌肉通常也具有这种直接驱动能力。

生命周期: 在失效前人工肌肉的激励-响应循环运动周期数量。

此外, 人工肌肉的能量密度、工艺复杂性、锁止负载、重复性精度、变刚度能力等也是在具体应用时需要考虑的性能指标^[11-12]。

面向未来的仿生机器人系统^[13-15], 人工肌肉研究具有多学科交叉的特点; 得益于材料、化学、生物、机械、电气等各领域学者的共同努力, 已研制出多种不同驱动机理的人工肌肉。作者依据驱动机理的不同, 将人工肌肉分为流体压力驱动、热致变形驱动、电致变形驱动、可控活体肌肉组织驱动等类型(聚焦于柔软材料), 并对各类人工肌肉的驱动机理、发展历程、优势与局限、适合场景以及研究重难点进行介绍, 最后给出人工肌肉的研究展望。

1 人工肌肉分类

1.1 流体压力人工肌肉

流体压力驱动的人工肌肉主要有气动和液动两种类型, 他们都是通过弹性体腔内流体的压力迫使弹性体壁在期望的方向上产生变形^[16-18]。例如 McKibben 气动肌肉^[19]是在橡胶等弹性体外部套上一层编织网, 限制弹性体的径向膨胀, 从而迫使变形向长度方向发展, 如图 1 所示。此类人工肌肉的主要难点在于如何设计结构使变形集中在期望的运动方向上。目前主要通过纤维限制^[20]、差异化壁厚设计^[21], 折纸结构设计^[22-23]等方法来实现。

最早的气动人工肌肉可追溯到 20 世纪 60 年代美国医生 MCKIBBEN 设计的 McKibben 型充气肌肉, 该人工肌肉用来驱动假肢; 后来又出现了能实现伸缩弯扭的气动网络化结构人工肌肉^[24-25]; FESTO 公司设计的气动连续体机械臂 BionicSoftArm^[26]是气动肌肉应用的典型代表。近几年在计算机图形学与力学的交叉融合下气动网络结构实现了计算机辅助设计, 同时 4D 打印技术^[27]的

发展也助力了软体气动人工肌肉的发展。

相对其他驱动方式, 流体压力驱动的人工肌肉发展较为成熟, 在功率密度(高达 22 kW/kg)^[28]、负载能力、柔软性、寿命等方面优势比较明显, 但是驱动压力高(高达 4 MPa), 存在爆炸泄露危险(现已存在多种依靠真空压力来实现收缩运动的气动驱动器, 可以减少对密封和正压力的要求, 如图 1e、1f 所示^[29-30]); 需要提供压力源(如泵、压力罐)等外部装置, 使其体积较大; 快速响应时不够稳定; 迟滞明显^[30]。此类人工肌肉比较适合在有压力源、对运动速度要求不高、对其体积限制较小、需要柔顺性高的场合^[31-42], 比如工厂自动化作业中的柔性抓取^[31]、柔性外骨骼^[33-34]、水下机械臂^[35], 柔性手术机械臂^[36-37]等。

图 1 流体压力驱动人工肌肉

流体压力驱动人工肌肉未来的主要研究方向有：设计折纸结构实现定向形变并减小驱动压力；进行软体结构力学建模高效完成结构设计、实现特定运动；利用 3D 打印^[28-29]等新工艺实现复杂结构制备；与其他材料(如形状记忆聚合物等)结合形成功能更为丰富的可变方向与结构的人工肌肉^[27]；设计新型的压力源(例如通过液体的相变^[29]、电润湿原理^[32]、精确控制化学反应生成气体^[28, 43]等)提升驱动器性能及适应能力。

1.2 热致变形人工肌肉

材料在加热到特定温度附近时产生明显的宏观变形，称之为热致变形。其中形状记忆合金 (Shape memory alloy, SMA)或形状记忆聚合物(Shape memory polymer, SMP)、液晶弹性体(Liquid crystal elastomer, LCE)、纤维型聚合物等通过热导致分子晶格改变或者大分子链发生变形，产生宏观的形状变化。

1.2.1 基于相变的热致动材料

SMA 在热(或磁场)的激励下合金晶格结构发生转换，从而宏观上造成形状改变，它具有很高的能量密度(镍钛合金的能量密度高达 50 W/g)和负载应力(200 MPa)^[45]。但 SMA 是刚性金属部件，而同样基于形状记忆特性工作的 SMP 则为树脂基软材料，两者的主要性能对比如表 1 所示。

表 1 SMA 与 SMP 性能比较

性能	应变	应力	功率密度	导电	导热	响应速度	成本
SMA	小	很大	高	好	好	慢	高
SMP	大	大	较高	差	差	很慢	低

SMA 在航空航天、玩具、仿生机器人等领域已经获得工程应用。例如图 2a，手机摄像头光学防抖并联机构由 SMA 驱动，使得封装、设计难度和受控能力得到很大的改善。图 2b 为 SMA 驱动的仿蠕虫机器人。

(a) 华为手机摄像头光学防抖组件

(b) 蠕虫机器人^[45]

图 2 SMA 人工肌肉

LEA(液晶弹性体驱动)与上述两种类型的人工肌肉驱动机理类似。液晶弹性体^[46]由交联的主链液晶单元和(或)侧链液晶单元组成，但结构具有典型的柔性，总体交联密度低。当受到刺激时，液晶弹性体的取向程度能发生很大的改变。液晶弹性体的

宏观机械响应是棒状液晶单元破坏的结果。如图 3 所示，当液晶原为向列相时，液晶弹性体的分子链延长，而在各向同性相时，分子链恢复成原来的状态。液晶弹性体在由向列相转换成各向同性相时，其单独的分子链形变转变成宏观形变。

上述三种依赖材料相变驱动的人工肌肉响应频率均较低，主要是因为热交换过程耗时较长，而且都存在比较大的迟滞特性^[47-48](如 NiTi 合金约 5%^[48])。

图 3 热驱动的 LEA^[46]

1.2.2 纤维型热致动人工肌肉

纤维型人工肌肉的工作原理是：加热使纤维、膜、片等材料(如尼龙、聚氯乙烯等)发生热致膨胀，再利用特定结构(如鞘-芯结构、双金属片等)实现宏观上的力和位移输出。这种原理与生物肌肉的肌纤维束工作原理类似。

纤维型人工肌肉于 2014 年^[49]首次提出，近几年《Science》等期刊^[49-51]刊登了几种新型高效的纤维型人工肌肉：RAY 课题组^[52]为了提高纤维丝的膨胀系数，在丝线外部环绕一层聚合物 PEO-SO3 的“鞘”，利用电热或者气动来使纤维产生膨胀，称之为 Sheath-run Artificial Muscles，如图 4 所示。这一工作改善了前人设计的卷绕型人工肌肉芯部变形小、驱动力弱的问题^[49-50]，将功率密度提高至 4.44 W/g，是生物肌肉的几十倍。同样为提高纤维的膨胀系数，MIT 的 POLINA 课题组利用环烯烃共聚物弹性体(Cyclic olefin copolymer elastomer, COCE)和高密度聚乙烯(PE)的热膨胀系数不同，将它们叠加到一起形成类似“双金属片”结构的肌肉纤维。制作过程中纤维被预拉伸，完成后纤维自然卷绕成弹簧结构。这种人工肌肉输出力大，寿命长(10 万次)，如图 5 所示。法国 PHILIPPE 等利用聚乙烯醇纤维结的形状记忆功能，制备了具有较大锁止力的旋转式的人工肌肉纤维^[51]，并通过掺杂碳纳米管和石墨烯使其力学性能和驱动性能大幅度提高。图 6 展示了一种纤维卷绕型人工肌肉驱动的仿生机械手指，无须依赖复杂的机械装置。此外，自然界的很多纤维在外界刺激下都会产生变形，比如动物毛发遇水会发生溶

胀^[56], 这些原理也具有被开发为人工肌肉的潜力。

总体来说, 热致变形能够产生较大的驱动力, 而且封装体积较小。这对于一些需要大驱动力的场合非常合适。

图 4 “鞘-芯”结构的纤维人工肌肉^[53]

(a) 制备工艺过程

(b) 驱动演示

图 5 “双金属片结构”的肌肉纤维^[54]

图 6 纤维肌肉热驱动仿生机械手指^[60]

由于加热及冷却过程耗时较长, 导致其响应速率较慢; 且冷却过程中绝大部分能量以热量的形式耗散、无法再利用, 使其能量转换效率很低; 此外, 其热致应变通常也较小, 通常存在迟滞现象。

热致变形的人工肌肉以 SMA 最为成熟, 已经在航天机构、玩具驱动器、摄像头模组等场合得以应用; 纤维卷绕型人工肌肉以超过 1 000 的负载自重比受到高度重视; LCE 人工肌肉在虚拟触觉、智能结构等场合也具有广阔前景。此类人工肌肉的主要技术挑战在于如何实现高效快速的热量交换, 如何设计结构获得更高的输出效率。

1.3 电致应变人工肌肉

电致应变一般是指在电场作用下材料发生变形, 电致应变材料主要有介电弹性体(Dielectric

elastomer actuator, DEA)、离子聚合物-金属复合材料(Ion-exchange polymer metal composite, IPMC)、液压放大静电驱动器(Hydraulically amplified self-healing electrostatic, HASEL)等^[61]。

1.3.1 介电弹性体

2000 年斯坦福研究院的学者^[62]首次发表高应变、高应力的介电弹性体驱动器研究成果。DEA 是一种典型的电驱动人工肌肉材料, 它的基本原理是: 两片柔性电极(碳膏、纳米银等)中间包夹弹性聚合物薄膜(聚丙烯酸、硅橡胶等), 形成平面电容结构。两电极通入高压电后形成高压电场, 聚合物薄膜内部分子链被极化, 在库仑力作用下产生宏观的径向压缩和切向扩张, 如图 7 所示。

图 7 DEA 的工作原理

由于功率密度、应力、应变、响应速度及能量效率等指标较高^[63-65], DEA 被用于多种软体机器人, 如爬壁机器人^[66]、游泳机器人^[67]、爬行机器人^[68]、飞行机器人^[69], 奔跑机器人^[70], 超轻连续体机械臂^[71]等, 部分机器人如图 8 所示。DEA 的缺点是驱动电压较高(10~100 V/μm), 迟滞较明显^[64]。目前研究的重点是: 采用新工艺制备更薄的介电弹性体薄膜以降低驱动电压(EFPL 研究者采用先进工艺制备超薄 DE 薄膜, 将 DEA 的驱动电压降低至百伏量级^[72]); 采用多层堆叠方式提高驱动器的负载能力和整体功率密度^[73]; 研究力电失稳、自愈合^[74]等机理来提高驱动器寿命。

(a) 自愈 DEA^[74]

(b) DE 爬壁机器人^[66]

(c) DEA 驱动飞行机器人^[69]

(d) DEA 驱动的机器鱼^[67]

(e) DEA 驱动奔跑机器人^[70] (f) DEA 驱动连续机械臂^[71]

图 8 DEA 人工肌肉驱动的机器人

1.3.2 液压放大静电驱动器

当两个物体所带的电荷密度很大时，彼此间可产生远大于其自身重量的库仑力。但库仑力随距离呈平方衰减，因此当利用库仑力做驱动时，需要保证两个物体间的距离不能因驱动器对外做功而显著分离。针对库仑力的作用特性，学者们结合液体压力的放大原理，制备了一种新型驱动器，命名为“HASEL”（图 9），该驱动器负载自重比可达 200 以上，并具备自愈能力。利用该原理，文献[75]开发了一种单方向弯曲的柔性抓手。

(a) HASEL 肌肉驱动原理

(b) 透明 HASEL 负载能力

图 9 HASEL 人工肌肉^[76]

而英国布里斯托大学的 JONATHAN 课题组^[77]从提高介电常数的角度提高了 Maxwell 应力驱动的静电驱动器性能。如图 10 所示，电极间的高介电常数液体(如硅油)介电常数较高，也提高了介电层的耐压值，使得该驱动器的负载能力提高 100 倍以上。

图 10 液体电介质静电驱动器^[77]

1.3.3 IPMC

IPMC 是离子交换聚合物金属复合材料的简称，图 11 展示了其基本的工作原理^[78-79]：中间基体薄膜(Nafion 或 Flemion 膜)夹在两金属电极板之间，薄膜中溶有电解液离子。当电极间加载电压(1~5 V)后，电解液中的阴阳离子在电场作用下产生定向移动，这种离子定向移动形成了溶液的浓度梯度，使得溶剂也发生定向移动。

图 11 IPMC 工作原理^[78]

此原理与生物细胞膜的主动运输非常类似。这种定向的压力以及静电力造成宏观的弯曲变形。

IPMC 的驱动电压低，但功率密度小，电致应力小。此外，IPMC 内的电解液使其一直保持“潮湿”状态，因此更适合在水下环境应用。

1.4 活体组织人工肌肉

活体肌肉组织作为人工材料驱动器是更具有科幻色彩的研究领域。因为其他类型人工肌肉材料目前还无法达到生物肌肉的综合性能指标。此类人工肌肉的产生较晚，主要发展节点^[80]如图 12 所示。这一技术的发展一直伴随着工程伦理的拷问。目前可以利用的活体组织主要有细菌体、动物心肌、骨

骨骼肌细胞或组织块。由于单细菌体属微型机器人，这里不作讨论。

图 12 活体肌肉驱动器发展历程^[80]

各种动物的心肌细胞，如青蛙、白鼠等，受控于基因表达都是一定节律的自主收缩，因此难以实现位置控制^[1]，但在爬行、游泳^[81]等节律型机器人上可以获得较好的应用^[82]。美国 SAM 等(图 13)采用计算机辅助设计对非洲爪蟾心肌细胞组织进行改造(或称人工进化)，设计一种具有生命的自主机器人“Xenobot”^[83]。

图 13 可编程爪蟾心肌细胞驱动机器人 Xenobot^[83]

而动物的骨骼肌细胞没有自主的节律收缩，因此其可控性更好^[84-85]。日本科学家利用电刺激来控制活体骨骼肌肉组织并制成机械臂，如图 14 所示^[85]。

图 14 拮抗骨骼肌肌肉驱动生物机械混合机器人^[85]

相比动物的肌肉细胞，昆虫由于其进化遗传特点，其肌肉细胞对环境的适应能力更强，对 pH、

温度、渗透压、氧含量的指标的要求不苛刻，甚至能够在自然温度，不换营养介质条件下生存 90 天^[80]。

目前，活体肌肉的主要激励方式有电刺激^[84-85]、光刺激^[86]、浓度梯度刺激等。其中电刺激是目前的主流激励方式(图 15)，但是这种方式需要液体中插入电极，电极间电压会造成营养液的电解，也会破坏细胞内外的电解液平衡。光刺激是一种更有前景的激励方式，通过对细胞进行基因改造，能够实现更好的光应激性(图 16)。

图 15 光响应活体肌肉驱动人工水母^[84]

图 16 光响应人工活体肌肉^[86]

活体肌肉作为工程材料不仅面临严重的工程伦理约束，而且也极大地依赖生命科学与生物技术支持，目前处于初级探索阶段。表 2 列举了典型活体人工肌肉设计需要考虑的关键因素。如何为活体组织提供合适的营养环境，在肌肉细胞间组装神经、血管、胶原蛋白、信号蛋白等都是未来需要解决的挑战性问题。

表 2 哺乳动物与昆虫肌肉组织的培养环境与技术

生存环境	哺乳动物细胞	37 ℃, pH=7.4, 5% CO ₂
	昆虫细胞	26 ℃, pH=6.0~6.4
关键技术	肌肉结构设计、激励方式、细胞与组织工程、3D 打印工艺	

2 总结与展望

表 3 对比了各类型人工肌肉的主要性能。可以看出，各类型人工肌肉都无法达到生物肌肉的综合性能水平。纤维卷绕型人工肌肉，除能量效率外，其余指标均可以达到甚至超过生物肌肉。DEA 和 HASEL 等电致变形驱动在功率密度、能量效率和响应频率上具有优势，但是需要高电压源，电路系统占用空间较大；流体压力驱动虽然

展现了良好的功率密度以及应变能力，但需要高压流体源和控制阀等组件，不易实现整体的小型化。体外生物活性组织人工肌肉材料还仅仅处于萌芽阶段，在培养环境、驱动控制方面还有诸多挑战。

生物体大都是利用肌纤维收缩实现对外做功，例如骨骼肌，心肌等。其背后的力学机制可能是：细长结构体的抗拉刚度远大于其抗压刚度，

当肌纤维产生同样的变形时，收缩形式比膨胀形式产生更大的驱动力，因此生物肌肉在进化过程中选择了收缩形式。上述人工肌肉中，采用收缩形式的负压气动人工肌肉和纤维卷绕人工肌肉较膨胀形式的液体正压驱动和 IPMC 驱动而言，具有更大的驱动力，也验证了这一观点。在人工肌肉的未来发展中，可对收缩形式的驱动器给予更多关注。

表 3 典型人工肌肉的性能对比(典型值)

种类	应变(%)	应力/MPa	功率密度/(W/g)	响应速度/Hz	能量效率(%)	伸/缩	能源装置
流体压力 ^[7]	—	—	22	>30	30	伸展	泵、阀
SMA ^[7, 45]	5	300	50	3	1.3	均可	电阻热
纤维卷绕 ^[53-55]	<50	20	100	<7.5	1.3	收缩	电阻热
DEA ^[69]	>100	8	0.6	300	90	伸展	高压源
HASEL ^[75-76]	10	6	0.284	50	—	收缩	高压源
IPMC ^[7, 78]	40	50	0.02	20	30	伸展	低压直流
压电薄膜	0.1	—	0.17	500M	很低	—	高压源
体外活体肌肉 ^[1]	60	>10	0.05	<5	>90	收缩	无菌培养液

从能量转化角度来看，生物肌肉的运动是在生物酶的高效催化条件下发生的快速生化反应，蛋白质等生物大分子自组织形成的有序纳米微结构及机构变形使肌肉具有高的能量密度和能量转换效率。这种生化反应的主要能量来自肌肉组织内的三磷酸腺苷(Adenosine triphosphate, ATP)分解，其能量密度、能量转换效率、响应速度、自修复、自学习、实时变刚度等性能是现有人工材料望尘莫及的^[87]。此外，人工肌肉驱动器的激励源同时也是驱动源，这与生物肌肉也有本质的区别：生物肌肉利用组织液提供能量，利用生物电信号来控制运动，这些组织液也为生物肌肉提供了散热、自修复等能力。人工材料或能够达到生物肌肉的响应速度，或能够达到生物肌肉的负载能力，但是在整体(包括驱动源)功率密度方面都没有达到生物肌肉的水平。

3D 打印工艺^[88-90]在制备人工肌肉复杂微结构(例如纤维)方面展现了巨大优势。正如影视作品《西部世界》中的场景(图 17)，3D 打印技术对结构功能一体化、综合指标均衡、仿生程度更高的新一代机器人的研发具有划时代的意义。

综上分析，研发可媲美生物肌肉性能的智能材料或超材料、研发更先进的人工肌肉制备工艺，仍然是极具挑战的课题，需要材料、化工、机械、生物、电子、控制等多学科共同努力。

图 17 《西部世界》剧照-3D 打印人工肌肉

参 考 文 献

- [1] RICOTTI L, TRIMMER B, FEINBERG A W, et al. Biohybrid actuators for robotics: A review of devices actuated by living cells[J]. Science Robotics, 2017, 2(12): eaaq0495.
- [2] HUNTER I W, LAFONTAINE S. A comparison of muscle with artificial actuators[C]// Technical Digest IEEE Solid-State Sensor and Actuator Workshop. IEEE, 1992: 178-185.

- [3] HUGHES D, HECKMAN C, CORRELL N. Materials that make robots smart[J]. The International Journal of Robotics Research, 2019, 38(12-13): 1338-1351.
- [4] HINES L, PETERSEN K, LUM G Z, et al. Soft actuators for small - scale robotics[J]. Advanced Materials, 2017, 29(13): 1603483.
- [5] HILLEBRANDT-ANDRADE C G. Minimizing caribbean tsunami risk[J]. Science, 2013, 341(6149): 966-968.
- [6] AKHRAS G. Smart materials and smart systems for the future[J]. Canadian Military Journal, 2000, 1(3): 25-31.
- [7] MIRVAKILI S M, HUNTER I W. Artificial muscles: Mechanisms, applications, and challenges[J]. Advanced Materials, 2018, 30(6): 1704407.
- [8] ZHANG J, SHENG J, O'NEILL C T, et al. Robotic artificial muscles : Current progress and future perspectives[J]. IEEE Transactions on Robotics, 2019, 35(3): 761-781.
- [9] MIRFAKHRAI T, MADDEN J DW, BAUGHMAN R H. Polymer artificial muscles[J]. Materials Today, 2007, 10(4): 30-38.
- [10] TRIVEDI D, RAHN C D, KIER W M, et al. Soft robotics: Biological inspiration, state of the art, and future research[J]. Applied Bionics and Biomechanics, 2008, 5(3): 99-117.
- [11] LASCHI C, MAZZOLAI B, CIANCHETTI M. Soft robotics : Technologies and systems pushing the boundaries of robot abilities[J]. Sci. Robot, 2016, 1(1): eaah3690.
- [12] 张忠强, 邹娇, 丁建宁, 等. 软体机器人驱动研究现状[J]. 机器人, 2018, 40(5): 74-85.
ZHANG Zhongqiang, ZOU Jiao, DING Jianning, et al. Research status of the soft robot driving[J]. Robot, 2018, 40(5): 648-659.
- [13] MOUTHUY P A, CARR A. Growing tissue grafts on humanoid robots : A future strategy in regenerative medicine?[J]. Science Robotics, 2017, 2(4): eaam5666.
- [14] MADDEN JDW, VANDESTEER N A, ANQUETIL P A, et al. Artificial muscle technology: Physical principles and naval prospects[J]. IEEE Journal of Oceanic Engineering, 2004, 29(3): 706-728.
- [15] CHRISTENSEN H I, OKAMURA A, MATARIC M, et al. Next generation robotics[J]. arXiv preprint arXiv, 2016: 1606.09205.
- [16] WANG T. Soft robotics: Structure, actuation, sensing and control[J]. Journal of Mechanical Engineering, 2017, 53(13): 1.
- [17] OHTA P, VALLE L, KING J, et al. Design of a lightweight soft robotic arm using pneumatic artificial muscles and inflatable sleeves[J]. Soft Robotics, 2018, 5(2): 204-215.
- [18] HAN K, KIM N H, SHIN D. A novel soft pneumatic artificial muscle with high-contraction ratio[J]. Soft Robotics, 2018, 5(5): 554-566.
- [19] CHOU C P, HANNAFORD B. Measurement and modeling of McKibben pneumatic artificial muscles[J]. IEEE Transactions on Robotics and Automation, 1996, 12(1): 90-102.
- [20] CONNOLLY F, WALSH C J, BERTOLDI K. Automatic design of fiber-reinforced soft actuators for trajectory matching[J]. Proceedings of the National Academy of Sciences of the United States of America, 2017, 114(1): 51-56.
- [21] GU G, WANG D, GE L, et al. Analytical modeling and design of generalized pneu-net soft actuators with three-dimensional deformations[J]. Soft Robotics, 2020(8): 19.
- [22] KIM W, BYUN J, KIM J K, et al. Bioinspired dual-morphing stretchable origami[J]. Science Robotics, 2019, 4(36): eaay3493.
- [23] LEE J G, RODRIGUE H. Origami-based vacuum pneumatic artificial muscles with large contraction ratios[J]. Soft Robotics, 2019, 6(1): 109-117.
- [24] MOSADEGH B, POLYGERINOS P, KEPLINGER C, et al. Pneumatic networks for soft robotics that actuate rapidly[J]. Advanced Functional Materials, 2014, 24(15): 2163-2170.
- [25] CHANG B, CHEW A, NAGHSHINEH N, et al. A spatial bending fluidic actuator: Fabrication and quasi-static characteristics[J]. Smart Materials and Structures, 2012, 21(4): 45008.
- [26] BionicSoftArm | Festo[OL]. <https://www.festo.com/group/zh/cms/13527.htm>.
- [27] ZHANG Z, DEMIR K G, GU G X. Developments in 4D-printing: A review on current smart materials, technologies, and applications[J]. International Journal of Smart and Nano Materials, 2019, 10(3): 205-224.
- [28] JARDINE J G, OTA T, SOK D, et al. A 3D-printed, functionally graded soft robot powered by combustion[J]. Science, 2015, 349(6244): 156-161.

- [29] MIRIYEV A, STACK K, LIPSON H. Soft material for soft actuators[J]. *Nature Communications*, 2017, 8(1): 1-8.
- [30] YANG D, VERMA M S, SO J H, et al. Buckling pneumatic linear actuators inspired by muscle[J]. *Advanced Materials Technologies*, 2016, 1(3): 1600055.
- [31] TRUBY R L, WEHNER M, GROSSKOPF A K, et al. Soft somatosensitive actuators via embedded 3D printing[J]. *Advanced Materials*, 2018, 30(15): e1706383.
- [32] CACUCCIOLO V, SHINTAKE J, KUWAJIMA Y, et al. Stretchable pumps for soft machines[J]. *Nature*, 2019, 572(7770): 516-519.
- [33] ROBERTSON M A, SADEGHI H, FLOREZ J M, et al. Soft pneumatic actuator fascicles for high force and reliability[J]. *Soft Robotics*, 2017, 4(1): 23-32.
- [34] 王琦珑, 王伟, 郝大贤, 等. 编织型气动人工肌肉迟滞现象建模与应用[J]. *机械工程学报*, 2019, 55(21): 73-80.
- WANG Qilong, WANG Wei, HAO Daxian, et al. Hysteresis modeling and application of mckibben pneumatic artificial muscles[J]. *Journal of Mechanical Engineering*, 2019, 55(21): 73-80.
- [35] HAO Y, GONG Z, XIE Z, et al. Universal soft pneumatic robotic gripper with variable effective length[C] // Staff, I. 2016 35th Chinese Control Conference (CCC). Piscataway: IEEE, 2016: 6109-6114.
- [36] ASBECK A T, SCHMIDT K, WALSH C J. Soft exosuit for hip assistance[J]. *Robotics and Autonomous Systems*, 2015, 73: 102-110.
- [37] ASBECK A T, ROSSI S M M de, HOLT K G, et al. A biologically inspired soft exosuit for walking assistance[J]. *The International Journal of Robotics Research*, 2015, 34(6): 744-762.
- [38] LASCHI C, CIANCHETTI M, MAZZOLAI B, et al. Soft robot arm inspired by the octopus[J]. *Advanced Robotics*, 2012, 26(7): 709-727.
- [39] CHEN Y. Design, fabrication and performance of a flexible minimally invasive surgery manipulator integrated with soft actuation and variable stiffness[J]. *Journal of Mechanical Engineering*, 2018, 54(17): 53.
- [40] CHANG B C-M, BERRING J, VENKATARAM M, et al. Bending fluidic actuator for smart structures[J]. *Smart Materials and Structures*, 2011, 20(3): 35012.
- [41] ZHU M, DO T N, HAWKES E, et al. Fluidic fabric muscle sheets for wearable and soft robotics[J]. *Soft Robotics*, 2020, 7(2): 179-197.
- [42] ZHANG J, SIMEONOV A, YIP M C. Three-dimensional hysteresis compensation enhances accuracy of robotic artificial muscles[J]. *Journal of Micromechanics and Microengineering*, 2018, 27(3): 35002.
- [43] WEHNER M, TRUBY R L, FITZGERALD D J, et al. An integrated design and fabrication strategy for entirely soft, autonomous robots[J]. *Nature*, 2016, 536(7617): 451-455.
- [44] RANZANI T, RUSSO S, BARTLETT N W, et al. Increasing the dimensionality of soft microstructures through injection-induced self-folding[J]. *Advanced Materials*, 2018, 30(38): e1802739.
- [45] RODRIGUE H, WANG W, HAN M-W, et al. An overview of shape memory alloy-coupled actuators and robots[J]. *Soft Robotics*, 2017, 4(1): 3-15.
- [46] HE Q, WANG Z, WANG Y, et al. Electrically controlled liquid crystal elastomer - based soft tubular actuator with multimodal actuation[J]. *Science Advances*, 2019, 5(10): eaax5746.
- [47] SIMONE F, RIZZELLO G, SEELECKE S. Metal muscles and nerves—a self-sensing SMA-actuated hand concept[J]. *Smart Materials and Structures*, 2017, 26(9): 95007.
- [48] MERTMANN M, VERGANI G. Design and application of shape memory actuators[J]. *The European Physical Journal Special Topics*, 2008, 158(1): 221-230.
- [49] ALCAIDE J O, PEARSON L, RENTSCHLER M E. Design, modeling and control of a SMA-actuated biomimetic robot with novel functional skin[C]// 2017 IEEE International Conference on Robotics and Automation (ICRA). IEEE, 2017: 4338-4345.
- [50] PANKSEPP J. Playing nature's game with artificial muscles[J]. *Science*, 2005, 308(5718): 62-63.
- [51] FOROUGH J, SPINKS G. Carbon nanotube and graphene fiber artificial muscles[J]. *Nanoscale Advances*, 2019, 1(12): 4592-4614.
- [52] GAO P, LI J, SHI Q. A hollow polyethylene fiber-based artificial muscle[J]. *Advanced Fiber Materials*, 2019, 1(3-4): 214-221.
- [53] MU J, DE ANDRADE M J, FANG S, et al. Sheath-run artificial muscles[J]. *Science*, 2019, 365(6449): 150-155.
- [54] KANIK M, ORGUC S, VARNAVIDES G, et al. Strain-programmable fiber-based artificial muscle[J]. *Science*, 2019, 365, 145-150.
- [55] HAINES C S, LIMA M D, LI N, et al. Artificial muscles

- from fishing line and sewing thread[J]. *Science*, 2014, 343(6173): 868-872.
- [56] MIRVAKILI S M, PAZUKHA A, SIKKEMA W, et al. Niobium nanowire yarns and their application as artificial muscles[J]. *Advanced Functional Materials*, 2013, 23(35): 4311-4316.
- [57] YUAN J, NERI W, ZAKRI C, et al. Shape memory nanocomposite fibers for untethered high-energy microengines[J]. *Science*, 2019, 365(6449): 155-158.
- [58] SHIN B, HA J, LEE M, et al. Hygrobot: A self-locomotive ratcheted actuator powered by environmental humidity[J]. *Science Robotics*, 2018, 3(14): eaar2629.
- [59] WHITE T J, BROER D J. Programmable and adaptive mechanics with liquid crystal polymer networks and elastomers[J]. *Nature Materials*, 2015, 14(11): 1087-1098.
- [60] WU L, JUNG DE ANDRADE M, SAHARAN L K, et al. Compact and low-cost humanoid hand powered by nylon artificial muscles[J]. *Bioinspiration & Biomimetics*, 2017, 12(2): 26004.
- [61] BOLZMACHER C, BIGGS J, SRINIVASAN M. Smart structures and materials 2006: Electroactive polymer actuators and devices (EAPAD)[J]. *Proc. SPIE*, 2006, 6168: 27-38.
- [62] PELRINE, KORNBLUH, PEI, et al. High-speed electrically actuated elastomers with strain greater than 100%[J]. *Science*, 2000, 287(5454): 836-839.
- [63] O'HALLORAN A, O'MALLEY F, MCHUGH P. A review on dielectric elastomer actuators, technology, applications, and challenges[J]. *Journal of Applied Physics*, 2008, 104(7): 71101.
- [64] ANDERSON I A, GISBY T A, MCKAY T G, et al. Multi-functional dielectric elastomer artificial muscles for soft and smart machines[J]. *Journal of Applied Physics*, 2012, 112(4): 41101.
- [65] 李铁风, 李国瑞, 梁艺鸣, 等. 软体机器人结构机理与驱动材料研究综述[J]. *力学学报*, 2016, 48(4): 756-766.
- LI Tiefeng, LI Guorui, LIANG Yiming, et al. Review of materials and structures in soft robotics[J]. *Chinese Journal of Theoretical and Applied Mechani*, 2016, 48(4): 756-766.
- [66] GU G, ZOU J, ZHAO R, et al. Soft wall-climbing robots[J]. *Science Robotics*, 2018, 3(25): eaat2874.
- [67] LI T, LI G, LIANG Y, et al. Fast-moving soft electronic fish[J]. *Science Advances*, 2017, 3(4): e1602045.
- [68] RIVAZ S D de, GOLDBERG B, DOSHI N, et al. Inverted and vertical climbing of a quadrupedal microrobot using electroadhesion[J]. *Science Robotics*, 2018, 3(25): eaau3038.
- [69] CHEN Y, ZHAO H, MAO J, et al. Controlled flight of a microrobot powered by soft artificial muscles[J]. *Nature*, 2019, 575(7782): 324-329.
- [70] ZHAO J, ZHANG J, MCCOUL D, et al. Soft and fast hopping-running robot with speed of six times its body length per second[J]. *Soft Robotics*, 2019, 6(6): 713-721.
- [71] XING Z, ZHANG J, MCCOUL D, et al. A Super-lightweight and soft manipulator driven by dielectric elastomers[J]. *Soft Robotics*, 2020, 7(4): 512-520.
- [72] JI X, LIU X, CACUCCILO V, et al. An autonomous untethered fast soft robotic insect driven by low-voltage dielectric elastomer actuators[J]. *Science Robotics*, 2019, 4(37): eaaz6451.
- [73] DUDUTA M, HAJIESMAILI E, ZHAO H, et al. Realizing the potential of dielectric elastomer artificial muscles[J]. *Proceedings of the National Academy of Sciences of the United States of America*, 2019, 116(7): 2476-2481.
- [74] LI C H, WANG C, KEPLINGER C, et al. A highly stretchable autonomous self-healing elastomer[J]. *Nature Chemistry*, 2016, 8(6): 618-624.
- [75] PARK T, KIM K, OH S R, et al. Electrohydraulic actuator for a soft gripper[J]. *Soft Robotics*, 2019, 7(1): 68-75.
- [76] KELLARIS N, VENKATA V G, SMITH G M, et al. Peano-HASEL actuators: Muscle-mimetic, electrohydraulic transducers that linearly contract on activation[J]. *Science Robotics*, 2018, 3(14): eaar3276.
- [77] TAGHAVI M, HELPS T, ROSSITER J. Electro-ribbon actuators and electro-origami robots[J]. *Science Robotics*, 2018, 3(25): eaau9795.
- [78] SHAHINPOOR M, BAR-COHEN Y, SIMPSON J O, et al. Ionic polymer-metal composites (IPMCs) as biomimetic sensors, actuators and artificial muscles-a review[J]. *Smart Materials and Structures*, 1998, 7(6): R15.
- [79] KHAWWAF J, ZHENG J, CHAI R, et al. Adaptive microtracking control for an underwater IPMC actuator using new hyperplane-based sliding mode[J]. *IEEE/ASME Transactions on Mechatronics*, 2019, 24(5):

- 2108-2117.
- [80] APPIAH C, ARNDT C, SIEMSEN K, et al. Living materials herald a new era in soft robotics[J]. *Advanced Materials*, 2019, 31(36): e1807747.
- [81] HERR H, DENNIS R G. A swimming robot actuated by living muscle tissue[J]. *Journal of Neuroengineering and Rehabilitation*, 2004, 1(1): 6.
- [82] RIVERA-TARAZONA L K, et al. Shape-morphing living composites[J]. *Science Advances*, 2020, 6(3): eaax8582.
- [83] KRIEGMAN S, BLACKISTON D, LEVIN M, et al. A scalable pipeline for designing reconfigurable organisms[J]. *Proceedings of the National Academy of Sciences*, 2020, 117(4): 1853-1859.
- [84] NAWROTH J C, LEE H, FEINBERG A W, et al. A tissue-engineered jellyfish with biomimetic propulsion[J]. *Nature Biotechnology*, 2012, 30(8): 792-797.
- [85] MORIMOTO Y, ONOE H, TAKEUCHI S. Biohybrid robot powered by an antagonistic pair of skeletal muscle tissues[J]. *Science Robotics*, 2018, 3(18): eaat4440.
- [86] SAKAR M S, NEAL D, BOUDOU T, et al. Formation and optogenetic control of engineered 3D skeletal muscle bioactuators[J]. *Lab on a Chip*, 2012, 12(23): 4976-4985.
- [87] RAGAUSKAS A J, WILLIAMS C K, DAVISON B H, et al. The path forward for biofuels and biomaterials[J]. *Science*, 2006, 311(5760): 484-489.
- [88] SUNDARAM S, SKOURAS M, KIM D S, et al. Topology optimization and 3D printing of multimaterial magnetic actuators and displays[J]. *Science Advances*, 2019, 5(7): eaaw1160.
- [89] SHEIKO S S, EVERHART M H, DOBRYNIN A V, et al. Encoding tissue mechanics in silicone[J]. *Science Robotics*, 2018, 3(18): eaat7175.
- [90] SKYLAR-SCOTT M A, MUELLER J, VISSER C W, et al. Voxellated soft matter via multimaterial multinozzle 3D printing[J]. *Nature*, 2019, 575(7782): 330-335.
- [91] Kumar A. Methods and materials for smart manufacturing : Additive manufacturing , internet of things , flexible sensors and soft robotics[J]. *Manufacturing Letters*, 2018, 15: 122-125.
-
- 作者简介：邢志广，男，1992 年出生，博士研究生。主要研究方向为软体驱动器，软体机器人变刚度技术。
E-mail: zhiguangx_hit@163.com
- 林俊，男，1997 年出生，硕士研究生。主要研究方向为软体机器人吸附技术。
E-mail: junlin_hit@163.com
- 赵建文(通信作者)，男，1978 年出生，博士，教授，博士研究生导师。主要研究方向为软体机器人、软传感器理论及工程应用。
E-mail: zhaojianwen@hit.edu.cn